

Activity 3

A nanoscale thermometry platform made by Dr. Estrada's group (see schematic) consists of a single crystal metal bar that is heated through Joule heating. The heater is made from an isomorphous binary alloy of 13.6 at.% Ni in 86.4 at.% Cu. The dimensions of the bar are 200 nm in width, 1000 nm in length, and 50.0 nm in height (thickness).

Note: at 300 K, $\rho_{\text{Cu}} = 17.1 \text{ n}\Omega \text{ m}$ and $\alpha_{\text{Cu}} = 4.00 \times 10^{-3} \text{ K}^{-1}$. The effective Nordheim coefficient of Ni dissolved in Cu is $C = 1310 \text{ n}\Omega \text{ m}$. At 100 K, the carrier mean free path for the alloy is $\lambda = 65.0 \text{ nm}$, the mean carrier speed is $1.60 \times 10^6 \text{ m/s}$, and the alloy's specularly parameter is 0.800.

When operating the device with an applied bias of 50.0 mV, the power dissipated in the heater must be 500 μW . Will the heater achieve the necessary power dissipation? If not, what recommendations would you make?

